

**STARGEL 350**

Stripping / conditioner

**DESCRIPTION**

Alkaline watery gel, combined with tense-actives and hydro-soluble solvents to remove ink and emulsion residues. Specially indicated to remove ghost image stains. It works as a pre-coated degreaser, too. Free of chlorine and chemical agents for the weave, it doesn't decrease the duration of the screens.

**CHARACTERISTICS**

Physical form	Gel
Colour	Cream
Odour	Tenuous
Corrosive	Yes
Flammable	No

**PACKAGING**

20 ltr. Box	20 unit x 1 ltr.
20 ltr. Box	4 unit x 5 ltr.
20 ltr. Drum	1 unit

**SAFETY CONDITIONS**

Corrosive product. Use gloves, goggles, ... See SAFETY DATA SHEET.

**INSTRUCTIONS OF USE**

Apply over dry screens with brush or squeeze always for both sides of the screen.

To obtaining the optimum efficiency of the product please see the following table:

MESH in cm	GHOST IMAGE and REMAINS OF INK	HARD EMULSION RECOVERY (HARDENED)
From 12 to 62 threads	5 / 15 min.	From 15 to 30 min.
From 68 to 90 threads	10 / 20 min.	From 20 to 40 min.
From 110 to 160 threads	10 / 30 min.	From 20 to 50min.

For high thickness (density) coated screens The recovery must between 45 min and 1 hour

Leave the screen in horizontal position. If is possible, at a temperature between 22 – 35°C.

Don't place the screen near a heat focus, **not upper to 35°C**.

**Avoid let dry the product over the screen because threads could be broken specially on fine mesh.**

Before washing out with water under pressure, remove the product with moderate water jet to avoid smell.

To eliminate persistent rests of emulsions or ghost image stains, make a second application of 10 min following the above instructions.

It is not necessary to have a completely dry screen, but water must be drained maximum.

**STARGEL 350 + STARGEL Activator**

If you wish to activate the STARGEL 350 more, you can add our **STARGEL Activator**. The advisable dissolution should be between 1:1

**ADDITIONAL INFORMATION**

---

Safety data sheet is available through Kopimask or your nearer supplier.

KOPIMASK, S.A. Ph. 00 34 93 863 93 50 Fax 00 34 93 864 70 37 e-mail [kopimask@kopimask.es](mailto:kopimask@kopimask.es)

The data here contained is the more accurate as possible, based on our present knowledge. Nevertheless, no guarantee regarding its reliability can be given as we cannot anticipate every possible application. For the same reason our products are sold without guarantee and under the condition that users will make their own tests in order to value if the product satisfies their necessities. KOPIMASK, S.A. reserves its rights to make any modifications without previous warning.



ISO 9001:2000 N°: E204216



[www.kopimask.com](http://www.kopimask.com)